#### THE WORLD LEADER IN CLEAN AIR SOLUTIONS

# SAAFCarb™ MA.HT

# **ENGINEERED CHEMICAL MEDIA**

- Ideal for H₂S removal
- Provides extended equipment protection with infrequent media changeovers
- Compatible for use in all carbon-based air filtration systems
- Low pressure drop and high adsorptive capacity

# **Engineered Media**

SAAFCarb MA.HT engineered gas removal chemical media is designed to have a high capacity for H<sub>2</sub>S and to efficiently remove multiple gaseous contaminants from airstreams. Target contaminants include:

- Hydrogen sulfide
- Chlorine
- Nitrogen dioxide
- Sulfur dioxide

SAAFCarb MA.HT is a high capacity chemical media targeted for  $H_2S$  removal. The media is composed of carbon and other proprietary ingredients specifically engineered to enhance  $H_2S$  capacity and to mitigate safety concerns associated with the use of metal oxide impregnated activated carbons, making this media safe before and during use. SAAFCarb MA.HT is the most cost-effective choice for removal of  $H_2S$  from an airstream.



SAAFCarb MA.HT media removes impure gases by adsorption, absorption, and chemical reaction. In the process, the reactive gases are trapped within the pellet, where a chemical reaction changes the gases into harmless solids and thereby mitigates the possibility of desorption.

## **Quality Control**

SAAFCarb MA.HT media undergoes the following quality control tests:

- Apparent Density
- Ball-pan Hardness
- H<sub>2</sub>S Gas Capacity
- Moisture Content
- Pellet Diameter





# SAAFCarb™ MA.HT Media

#### **Typical Properties**

Apparent density: 560 kg/m³ acc. ASTM D2854

Carbon description: Non-impregnated H<sub>2</sub>S gas capacity: 0,30g H<sub>2</sub> S/cc Hardness: 95% min

Nominal diameter: 3 mm

Shape: Cylindrical pellet

Disclaimer: Typical properties are produced using AAF and industry standard test methods. They are listed for informational purposes only and are not to be used as purchase specifications. Certificates of analysis are available for specific batches upon request.

### **Packaging Options and Application Guidelines**

#### **Packaging Options**

SAAFCarb MA.HT media is packaged in containers of 25 kg and big bags of 500 kg.

SAAFCarb MA.HT media is also available packaged in SAAF cartridges, cassettes, and trays.

#### **Application Guidelines**

SAAFCarb MA.HT media performs under the following application guidelines (actual capacities and efficiencies may vary):

Temperature: -20° to 50 °C
Humidity: 10% – 95% RH

• Airflow: From 40 m<sup>3</sup>/h to over 170.000 m<sup>3</sup>/h

• Velocity: From 0,30 to 2,5 m/s

# **Installation and Disposal Requirements**

#### Installation

The installers must use dust masks, safety goggles, and rubber gloves.

#### Disposal

The spent SAAFCarb MA.HT media must be disposed of according to local and federal guidelines. MSDS included in each shipment.

#### Safety

Wet activated carbon adsorbs atmospheric oxygen, causing low oxygen supply in enclosed areas or packed containers. This can be potentially hazardous for workers who enter these oxygen-depleted areas. Make sure that workers adhere to the provincial and state safety guidelines.

